













# 868-A : Spinel Mint	# 868-B : Spinel Mint	# 868-C : Spinel Mint
# 862-A : Spinel Turquoise	# 862-B : Spinel Turquoise	# 862-C : Spinel Turquoise
# 863-A : Spinel Blue	# 863-B : Spinel Blue	# 863-C : Spinel Blue
# 855-A : Ultramarine Blue	# 855-B : Ultramarine Blue	# 855-C : Ultramarine Blue
# 655-A : Ottamarine blue	# 655-b : Ottramarine blue	# 655-C : Ottramanine blue
#856-A : Ultramarine Violet	# 856-B : Ultramarine Violet	# 856-C : Ultramarine Violet
# 850-A : Iron-Oxide Black	# 850-B : Iron-Oxide Black	# 850-C : Iron-Oxide Black
# 050-A ; ITON-OXIDE BIACK	# 000-D ; ITUII-UXIDE BIACK	# 000-C ; ITOII-OXIDE BIACK



Quantities for mixing		
A	В	C

Clay Paint

7.5 kg of powder	7.5 kg of powder	7.5 kg of powder
750 g of pigment	265 g of pigment	60 g of pigment
(to be diluted in water)	(to be diluted in water)	(to be diluted in water)

Lime Paint (smooth and textured)

10 L of paint	10 L of paint	10 L of paint
1 kg of pigment	350 g of pigment	75 g of pigment
(to be diluted in water)	(to be diluted in water)	(to be diluted in water)

GekkkoSOL Paint (smooth and 0.5 mm)

5 L of paint	5 L of paint	5 L of paint
500 g of pigment	175 g of pigment	40 g of pigment
(to be diluted in GekkkoSOL thinner)	(to be diluted in GekkkoSOL thinner)	(to be diluted in GekkkoSOL thinner)

Lime Wall Plasters (0.5 mm, 0.9 mm, 1.4 mm)

10 kg of powder	10 kg of powder	10 kg of powder
500 g of pigment	175 g of pigment	40 g of pigment
(to be diluted in water)	(to be diluted in water)	(to be diluted in water)

Stucco and Marmorino

10 kg of powder	10 kg of powder	10 kg of powder
380 g of pigment	150 g of pigment	40 g of pigment
(to be diluted in water)	(to be diluted in water)	(to be diluted in water)

Tadelakt

10 kg of powder	10 kg of powder	10 kg of powder
240 g of pigment	100 g of pigment	24 g of pigment
(to be diluted in water)	(to be diluted in water)	(to be diluted in water)

Before using any products, consult their technical data sheets available under the 'Technical Data' tab in every product pages.

Tipsheet: How to mix natural dry pigments with paints or plasters